

Nominal Weight	5.3 osy (200 gsm)
Fiber Blend	Modacrylic / Nylon / Lyocell
Made in America	Yes
Flame Resistance	ASTM D 6413
<p>Before Laundering</p> <p>after flame after glow char length melt / drip</p> <p>100x After Wash</p> <p>after flame after glow char length melt / drip</p>	<p>0 sec <10 x <10 sec <7.5 x <7.5 in none</p> <p>0 sec <10 x <10 sec <7.5 x <7.5 in none</p>
Predicted Body Burn	3 sec Flash Fire Exposure ASTM F 1930
2nd Degree Burn	26.5%
3rd Degree Burn	6.5%
Total Body Burn	32%
TPP	NFPA 2112
with spacer	11
without spacer	8
Breaking Strength	ASTM D 5034
before laundering	105 x 70 lbf
laundered 25x	95 x 65 lbf
Air Permeability ASTM 737	75 ft ³ /ft ² /min
MVTR	1500 g/m ² /24hr
Dimensional Stability AATCC 135 , 3, V, Aiii	<3 x 3%